


CERIUM OXIDE BASED GLASS POLISHING COMPOUND

Typical Physical Properties

- **Appearance** orange-brown powder
- **pH** 7.0 – 9.0
- **Particle Size (coulter)**
 - D50..... 1.3 – 2.8 μ m
 - D0..... 18.0 μ m max
- **Composition**
 - TREO 80 - 86%
- **Suspension Treated** yes

Applications

- ✓ **Designed for polishing Ophthalmic Glass**
 - spheric
 - toric
- ✓ **Ophthalmic mold polish**



Output: Coulter Multisizer

- **Packaging**.....44 lbs/pail; 1584 lbs/pallet
 55 lbs/box; 1980 lbs/pallet
 525 lbs/drum; 2100 lbs/pallet
- **Cautions**.....Refer to Material Safety Data Sheet

The information herein is considered to be a fair representation of this product. The data are not to be interpreted as a specification or guarantee of properties. Ferro Corporation makes no implied warranties as to its accuracy and assumes no liability arising out of its use by others. The information does not constitute a license to use or infringe any patents.